

GYPSUM PUTTY MAX

Product code: PW2509

Composition and Application Field

NOVA Gypsum Putty Max is a specially designed water based composite base on an acrylic copolymer and suitable pigments, filler with good alkali resistance. It is primarily used for use on gypsum boards, spray plasters, and other cementitious compositions, to give an even surface for subsequent painting after filling surface irregularities, construction flaws, hairline surface cracks & indentations. It has got sufficient plasticizing properties to make it suitable for a reasonably thick application which will not peel off or flake after drying.

Use

Substrates: Gypsum, Gypsum boards, Spray plasters, and certain wood applications.

Area of Use: Interiors only

Specification

Finish	: Smooth & Buttery
Colour	: White to off White
Specific gravity	: 1.70 ± 0.02
Solids (% by volume)	: 52 ± 2
Diluent	: Sweet Water
Flash point	: Not Applicable

Spread Rate:

While the spread rate is directly dependent on the surface profile, and also the undulations it has, as a thumb rule

NOVA Gypsum Max would cover app. 3 - 4 square meters per Kg and may be taken for cost calculations.

Drying Time (30° C) : Set to touch: 30 minutes- 1 hour.
: Ready for Recoat: app 3- 4 hours

Recommended DFT : 1-2 coats. App 100 – 150 mic per coat

Surface Preparation

A good surface preparation and following the method statement / recommended system procedure of NOVA is an ideal recommendation for the application of **NOVA Gypsum Max**.

For Gypsum, Spray Plaster & Masonary :

Achieve a good and clean surface by removing all contaminants by cleaning & drying. A laitance free surface should be achieved by good sweep blast or a wire brush. Before applying the **NOVA Gypsum Putty Max** apply one coat of **NOVA PVA Primer Sealer** and allow drying.

For usage on Wood & Timber:

Achieve a good and clean surface by removing all contaminants by cleaning & drying treatment with NOVA Wood Preservative Compound is advisable.

Start off with good coat of **NOVA Wood Primer** and allow to dry well and apply required coats of **NOVA Gypsum Putty Max**. Exclusions for successful application include perpetually wet surfaces and also large cavities on wooden surfaces.

Application Method

Adequate ventilation is an ideal situation as it helps in drying and the good application itself. Avoid high humid conditions i.e., >95% when condensation is likely to interfere and also when the surface temperature is at least 3°C above dew point. One can add 5 to 10% of sweet water for ease of application depending on the suitability of application. One should apply with a putty knife or a board bladed knife and spread it evenly on the surface to smoothen. After application light sanding may done to remove the imperfections.

HANDLING

Disposal: As per the guidance and legislations of the local Authority e.g., by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Not applicable

Safety Precaution

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapors or spray. MSDS is available on request for the safe handling of this product.

FIRST AID

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved Industrial cleaner. DO NOT USE solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.